Technical Information

SUBSEAL-40

SELF-ADHERING WATERPROOFING MEMBRANE

DESCRIPTION

SubSeal-40[™] is a prefabricated self-adhering sheet-type waterproofing membrane. It is composed of a tough multi-layer cross-laminated film that is coated with a rubberized asphalt adhesive. A release liner protects the adhesive and is removed as the membrane is installed. SubSeal-40™ is intended as a multi-purpose waterproofing membrane for use in sub-grade applications and under siding, exterior plaster, as a through wall flashing or anywhere it will be protected from long-term ultraviolet exposure. SubSeal-40™ adheres aggressively to most clean, dry substrates including metal, wood vinyl, masonry, ICF foundations, Gold Bond® e²XP™ and rigid insulation boards. SubSeal-40™ may be used to waterproof foundations and other below grade structures, plaza decks, balconies, under siding, and exterior plaster. This advanced system bonds to the substrate and selfseals around nails, staples and other fasteners to prevent damage caused by water penetration.

MFM Building Products Corp. manufactures a wide range of innovative waterproofing products for the building industry. With more than 50 years of field experience, MFM products are

engineered for superior performance and ease of installation.

USES

Foundation wall, floor and planter waterproofing, under stucco and at head, sill chimney shoulder, pot shelves, parapets and pony walls. Use for sealing SIPS building panels and around doors, windows and other potential leak areas. Waterproofs and protects ICF foundations from damage.

FEATURES

SubSeal-40™ offers the contractor and property owner these extra features:

- Uniform thickness for dependable protection
- Self-seals around fasteners including nails, staples and screws
- High strength, high elongation, flexible accommodates expansion and contraction of the substrates
- Protects ICF foundations and insulation boards from damage during backfill
- Outer film surface is compatible with most construction sealants
- Eliminates leaks multiple layers of protection seal out water
- Rubberized asphalt won't crack or dry
- Aggressively adheres SubSeal-40™ sticks in cool weather to common building materials for ease of application and to eliminate movement of water under the membrane

INSTALLATION

- Apply in clear, dry weather
- Surface must be clean, dry and free from oil
- Masonry must be clean, fully cured and primed with an asphalt primer
- Prime weathered surfaces and OSB as necessary
- Clean, dry wood and metal surfaces do not require priming
- Use 3" side laps and 6" head laps
- When applying on vertical concrete surfaces, a termination bar is recommended around the top
- Apply uniform pressure with a 2-3" hand roller to entire surface
- DO NOT install over solvent-based sealants unless fully cured active solvents may liquefy bottom adhesive surface
- Installer is responsible for compatibility with caulks and sealants
- DO NOT install over flexible vinyl gaskets or uncured caulking
- DO NOT expose installed product to direct sunlight for more than 90 days

PRODUCT DATA

| Installation Temperature Range | >50°F |
|--------------------------------|---------------------------|
| Material Color | Black |
| Roll Widths | 4", 6", 9", 12", 18", 36" |
| Roll Length | 75 ft |
| Carton Weight | 62 lbs |
| Rolls per Carton | 9, 6, 4, 3, 2, 1 |
| Area per Carton | 225 ft ² |
| Cartons per Pallet | 25 |

TECHNICAL SPECIFICATIONS

| Property | Test Method | Result |
|--------------------|--------------|----------------------|
| Material Thickness | ASTM D 1970 | 40 Mils Nom. |
| Pliability | ICC-ES AC 38 | Pass |
| Vapor Permeance | ASTM E 96 | 0.02 g/m² in 24h Max |
| Water Resistance | ASTM D 779 | >30 hr. |
| Nail Sealability | ASTM D 1970 | Pass |
| Tensile MD | ASTM D 882 | 21 lbf/in |
| Tensile CMD | ASTM D 882 | 28 lbf/in |

PRODUCT NUMBERS

| 36" - 51336 |
|-------------|
| 18" - 51318 |
| 12" - 51312 |
| 9" - 51309 |
| 6" - 51306 |

APPROVALS

SubSeal-40™ is tested to ICC-ES AC38, ASTM, ICC-ES ESR 2783





10-YEAR LIMITED WARRANTY

MFM Building Products Corp. (MFM) warrants materials to be free from leaks caused by defects in material or manufacturing for a period of ten (10) years from the date of purchase when applied according to published directions.



For the most current Installation Instructions, Warranties, Technical Specifications and Approvals, visit www.mfmbp.com.





Technical Information











